



SCM[®]
SuperCorrMedium



The mark of
responsible forestry



Papelera Nacional S.A.

ESPECIFICACIONES TECNICAS DE PAPEL LINER PANASA

Peso Básico	Standard	140	150	170	175	205	230	240	250	260	270
Tappi T410	Mínimo	137	146	165	170	200	225	235	245	254	264
(g/m ²)	Máximo	143	154	175	180	210	235	245	255	266	276

		140	150	170	175	205	230	240	250	260	270
Humedad	Estándar	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5
Tappi T412	Mínimo	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0	6,0
(%)	Máximo	9,0	9,0	9,0	9,0	9,0	9,0	9,0	9,0	9,0	9,0

		140	150	170	175	205	230	240	250	260	270
Calibre											
Tappi T411	Mínimo	0,19	0,21	0,23	0,24	0,27	0,33	0,34	0,35	0,36	0,37
(mm)	Máximo	0,30	0,32	0,34	0,35	0,38	0,43	0,44	0,45	0,46	0,47

		140	150	170	175	205	230	240	250	260	270
SCT CD	Estándar (kN/m)	2,45	2,63	2,98	3,15	3,59	4,03	4,20	4,38	4,55	4,73
Tappi T826	Mínimo (kN/m)	2,17	2,33	2,64	2,71	3,18	3,57	3,72	3,88	4,03	4,19
	Estándar (lbf/in)	14,0	15,0	17,0	18,0	20,5	23,0	24,0	25,0	26,0	27,0
	Mínimo (lbf/in)	12,4	13,3	15,1	15,5	18,2	20,4	21,2	22,2	23,0	23,9

		140	150	170	175	205	230	240	250	260	270
Mullen	Estándar (psi)	60	65	68	69	75	80	101	105	109	115
Tappi T807	Mínimo (psi)	56	60	68	69	74	77	80	84	87	90
	Estándar (kPa)	414	448	469	476	517	552	696	724	752	793
	Mínimo (kPa)	386	414	469	476	510	531	552	579	600	621

		140	150	170	175	205	230	240	250	260	270
Cobb(120 seg.)	Máximo	40	40	40	40	40	40	40	40	40	40
Tappi T441	Mínimo	20	20	20	20	20	20	20	20	20	20
(g/m ²)											

