



The mark of responsible forestry



ESPECIFICACIONES TECNICAS DE PAPEL SCM - SUPER CORR MEDIUM

Peso Básico	Estándar	146	160	176	195
Tappi T410	Mínimo	142	156	171	190
(g/m ²)	Máximo	150	165	180	200

		146	160	176	195
Humedad	Estándar	7,5	7,5	7,5	7,5
Tappi T412	Mínimo	6,0	6,0	6,0	6,0
(%)	Máximo	9,0	9,0	9,0	9,0

		146	160	176	195
Calibre	Estándar	0,26	0,28	0,31	0,34
Tappi T411	Mínimo	0,20	0,22	0,24	0,27
(mm)	Máximo	0,31	0,34	0,37	0,41

			146	160	176	195
SCT CD	Estándar	(kN/m)	2,48	2,72	2,99	3,32
Tappi T826	Mínimo	(kN/m)	2,35	2,60	2,64	2,93
	Estándar	(lbf/in)	14,2	15,5	17,1	19,0
	Mínimo	(lbf/in)	13,4	14,8	15,1	16,7

			146	160	176	195
Concora (CMT)	Estándar	(kg)	34	36	38	40
Tappi T809	Mínimo	(kg)	30	32	34	36
	Estándar	(N)	333	353	372	392
	Mínimo	(N)	294	314	333	353

			146	160	176	195
Cobb (60 seg)	Máximo		50	50	50	50
Tappi T441	Mínimo		30	30	30	30
(g/m ²)						

